




PCT/AU2004/001365

Patent Office
Canberra

I, JULIE BILLINGSLEY, TEAM LEADER EXAMINATION SUPPORT AND SALES hereby certify that annexed is a true copy of the Provisional specification in connection with Application No. 2003905517 for a patent by SECURENCY PTY LIMITED as filed on 09 October 2003.



WITNESS my hand this
Eighteenth day of October 2004

A handwritten signature in cursive script, appearing to read 'J. Billingsley'.

JULIE BILLINGSLEY
TEAM LEADER EXAMINATION
SUPPORT AND SALES

BEST AVAILABLE COPY

AUSTRALIA

Patents Act 1990

PROVISIONAL SPECIFICATION

Invention Title: Security document with upconverting material

The invention is described in the following statement:

SECURITY DOCUMENT WITH UPCONVERTING MATERIAL

This invention relates to security documents and is particularly concerned with providing a security document with a covert security device which is detectable in order to verify the authenticity of the security document.

5 As used herein, the term "security document" refers to any type of document or token for which authenticity is important, and includes within its scope documents and tokens of value, such as banknotes, cheques, travellers cheques, stock and share certificates, and tickets, and also identity documents and tokens, such as credit cards, identification cards, passports and the like.

10 The use of covert security devices for verification of security documents is well known. One example of a covert security device is a fluorescent ink applied to the surface of a security document and which emits light or luminesces when exposed to electromagnetic radiation of a particular wavelength, eg. ultra-violet (UV) light.

15 The use of "upconverting" materials as covert security devices in security documents has also been proposed. An "upconverting" material is a material which absorbs electromagnetic radiation of a low energy level, eg. infra-red, and emits electromagnetic radiation at higher energy level, such as visible light. This anti-stokes conversion of absorbed and emitted energy is caused by the
20 upconverting material absorbing two photons of low energy and promoting a single electron to a higher energy state. When the electron returns to its original stable energy level, the material emits a photon of an energy level that is higher than the individual energy of the two incident photons.

25 Upconverting materials generally have an unusual structure, and examples of such materials include crystals or glasses doped with ions of rare earth metals, such as ytterbium (Yb) or thulium (Tm). The energy level of the emitted photons, and hence, the wavelength of the light emitted from such upconverting materials is uniquely characteristic of the particular upconverting material used. This makes

upconverting materials of particular interest as covert security devices for the authentication of security documents.

Hitherto, there have been proposals to use inks containing upconverting materials as covert security devices in security documents. However, this has
5 suffered from the disadvantage that the upconverting ink applied to the surface of a security document is exposed to adverse conditions during use of the security document. Banknotes, for example, are subjected to significant wear during their lifetime in circulation. This can cause the signal emitted by the upconverting material to deteriorate over the lifetime of the security document. Also,
10 upconverting materials applied to surface of a document are subject to chemical attack.

Further, upconverting materials are expensive to manufacture and so they are used only sparingly when added to security inks. However, it is necessary to use a sufficient amount of upconverting material in the ink in order to generate a
15 signal which is sufficiently strong to be detected by appropriate apparatus. Thus, a security ink containing an upconverting material is not usually applied over the whole surface of the security document. This has the disadvantage that the signal emitted from the upconverting material is only detectable over the particular region of the banknote where the upconverting ink has been applied.

20 It is therefore desirable to provide a security document containing an upconverting material in which at least some of the disadvantages of the prior art are alleviated.

It is also desirable to provide a security document containing an upconverting material in which the signal strength of the signal from the
25 upconverting material is enhanced.

According to one aspect of the invention, there is provided a security document comprising a substrate including at least one layer of polymeric material containing an upconverting fluorescent material, and a coating containing a refractive pigment applied to the substrate, wherein when the security document is

exposed to electromagnetic radiation of a particular wavelength the upconverting material emits a signal of electromagnetic radiation of a correspondingly shorter wavelength and the coating containing the refractive pigment enhances the signal emitted by the upconverting material.

5 The substrate preferably includes a polymeric base layer. One example of such a base layer is a transparent biaxially oriented polymeric material of the type described in WO 83/00659. However, other types of base layers, for instance, of other polymeric materials, or even base layers of paper or fibrous materials, may be provided.

10 The substrate may also include one or more layers of polymeric material provided on the base layer. In this case, the upconverting material may be dispersed in either the base layer or in the at least one layer of polymeric material provided on the base layer.

 Preferably, the coating containing the refractive pigment is in intimate
15 contact with the at least one polymeric layer containing the upconverting material. This assists in amplifying the signal emitted by the upconverting material. This may be achieved by applying a refractive coating directly to at least one surface of a polymeric base layer containing the upconverting material. Alternatively, the refractive coating may be applied to the external surface of a layer of polymeric
20 material containing the upconverting material which is provided on the base layer. It is, however, possible for the refractive coating to be applied to the surface of a layer of polymeric material provided on a base layer, with the base layer containing the upconverting material, though in this case the signal emitted from the security document may not be as strong.

25 The coating containing the refractive pigment is preferably a highly refractive opacifying coating. The opacifying coating may comprise at least one refractive pigment dispersed in a polymeric or resin binder. For example, the coating may include a major proportion of a refractive pigment bound with a minor proportion of a heat-activated cross-linkable polymeric binder.

Conveniently, the refractive pigments and binders are selected to be substantially transparent to the excitation wavelengths used to excite the upconverting material. The refractive pigments are preferably selected such that the difference between the refractive index of the pigment and the refractive index of the substrate is large. The difference between the refractive index of the pigment and the refractive index of the binder is preferably also large. In a particularly preferred embodiment, the refractive index of the pigment is at least 0.3 greater than the refractive index of either the substrate or the binder.

Examples of suitable refractive pigments include titanium dioxide (TiO_2), calcium carbonate (CaCO_3), barium sulphate (BaSO_4) and zinc oxide (ZnO). Examples of suitable binders include acrylics, polyester and polyurethane or similar polymers. The polymeric material may be cross-linked by cross-linking materials such as isocyanates, melamine condensates and similar materials. The proportion of the cross-linking material is preferably chosen so as to improve the resistance of the coating without impairing its function as a flexible, heat resistant, printable surface.

According to another aspect of the invention, there is provided a method of manufacturing a security document comprising : providing a substrate having at least one layer of polymeric material; incorporating at least one upconverting material in the at least one layer of polymeric material; and applying a refractive coating to at least one surface of the substrate.

The upconverting material may be incorporated into the at least one layer of polymeric material in an extrusion process. This is particularly convenient for a security document which has a co-extruded base layer and/or at least one co-extruded polymeric layer provided on a base layer. The upconverting material is preferably present in small quantities in the polymeric material. In particular, for transparent substrates, the amount of upconverting material is preferably sufficiently small as to be substantially invisible in the transparent substrate. In one preferred embodiment, the concentration of upconverting material is not more than about 1% by weight of the polymeric material, and more preferably falls

substantially within the range from about 0.0025% to about 0.25% by weight of the polymeric material.

In the extrusion process, the upconverting material is preferably mixed uniformly with the co-extruded polymeric material as it passes through the extruder and dies. This assists in producing a uniform distribution of the upconverting material throughout the at least one layer of polymeric material. Suitable apparatus for achieving this may include : scroll dies and barrier or twin screw extruders, eg. of the Werner Pflader type. The upconverting material may be added to the polymeric material in the form of a masterbatch, for example through a loss-in-weight screw addition feeder.

Preferably, the upconverting material is mixed with the polymeric material, eg in an extruder barrel, at an elevated temperature. For materials such as polypropylene, typical extrusion temperatures may fall substantially within the range from about 230°C to 250°C

Any convenient upconverting material or materials may be used in the present invention. Examples of suitable upconverting materials include crystals, glasses or metal oxide nanopowders doped with ions of Lanthanides, eg. Er^{3+} , Tm^{3+} , Nd^{3+} , Ho^{3+} and Yb^{3+} , although crystals doped with ions of some transition metals, eg. Ti^{2+} , Ni^{3+} , Mo^{3+} and Re^{4+} have also been found to exhibit upconverting properties. Examples of crystals which may be doped with such ions include halides, such as RbMnCl_3 , CsMnCl_3 , CsMnBr_3 and Rb_2MnCl_4 , and tungstate crystals, such as $\text{NaY}(\text{WO}_4)_2$. Examples of suitable upconverting nanopowders include Al_2O_3 or yttrium aluminium garnet doped with Nd^{3+} or Ce^{3+} .

In the case of a biaxially oriented polymeric substrate, the crystal structure of the upconverting material is preferably selected so as not to cause voids or air bubbles (intrusions) during the stretching process of biaxial orientation.

According to a further aspect of the invention, there is provided a method of verifying the authenticity of a security document comprising:

providing a security document with at least one polymeric layer containing an upconverting fluorescent material;

providing the security document with at least one opacifying coating containing a refractive pigment;

- 5 exposing the upconverting material to electromagnetic radiation of a selected wavelength to excite the upconverting material; and

detecting a signal of electromagnetic radiation emitted from the excited upconverting material at a shorter wavelength than the wavelength selected to excite the upconverting material.

- 10 In one preferred embodiment, the electromagnetic radiation selected to excite the upconverting material is infra-red radiation, and the signal electromagnetic radiation emitted from the upconverting material falls within the visible spectrum. In this case an infra-red laser may be used to excite the upconverting material at the selected wavelength. It is, however, possible to use
15 an upconverting material which is excited by electromagnetic radiation in the visible spectrum and to emit signals of ultraviolet radiation.

- It will be appreciated, that by selection of particular upconverting materials which absorb and emit electromagnetic radiation at different wavelengths specific to the upconverting material selected, it is possible to provide a high degree of
20 security as it will be difficult for counterfeiters to reproduce the security documents containing the specific upconverting material selected.

Preferred embodiments of the invention will now be described, by way of example only, with reference to the accompanying drawings, in which:

Figure 1 is a sectional view through part of a security document in accordance with a first embodiment of the invention;

Figure 2 is a sectional view through a security document in accordance with a second embodiment of the invention; and

5 Figure 3 is a sectional view through a security document in accordance with a third embodiment of the invention.

The security document 1 shown in Figure 1 comprises a substrate 10 in the form of a transparent polymeric base layer 12, an opacifying coating 14 applied to each side of the base layer 12, and a layer of printed indicia 16 applied to the
10 opacifying coating 14 on each side of the document 1.

The base layer 12 contains an upconverting fluorescent material 18 dispersed uniformly throughout the transparent polymeric material forming the base layer 12. The upconverting material 18 is preferably of the type which absorbs electromagnetic radiation at a selected wavelength corresponding to a
15 low energy level, eg. infra-red radiation, and emits electromagnetic radiation at a shorter wavelength corresponding to a higher energy level, eg. in the form of visible light. The base layer 12 is preferably formed from a transparent biaxially oriented polymeric material, though other materials may be used.

The opacifying coatings 14 applied to opposite surfaces of the base layer
20 12 each comprises at least one refractive pigment, such as titanium dioxide, dispersed in a polymer or resin binder. As shown in Figure 1, the opacifying coatings 14 and the indicia 16 printed on the coatings 14 are applied to the transparent base layer 12 in such a manner as to cover the base layer 12 only partially, leaving an area 13 of the base layer 12 uncovered to form a transparent
25 portion or "window" 15 which allows light to pass through. The "window" 15 which allows light to pass through. The window 15 may include a security device 17,

such as an optically variable device (OVD), or an embossing, provided on at least one surface of the uncovered area 13 of the base layer 12. The security device 17 is therefore able to be inspected through the window 15 from both sides of the security document.

5 The upconverting material 18 is present in the base layer 12 in only small quantities so that it does not affect the transparency of the base layer 12. Preferably, the concentration of the upconverting material 18 is not more than about 1% by weight of the polymeric material forming the base layer 12, and more preferably falls within the range from about 0.0025% to 0.25% by weight of the
10 polymeric material.

 In use, when it is desired to verify the authenticity of the security document 1 an infra red source 20, such as an infra red laser, emitting infra red radiation of a chosen wavelength can be used to excite the upconverting material 18 in the base layer 12 causing it to emit visible light signals 22 of a particular wavelength which
15 depends upon the particular upconverting material 18 dispersed in the transparent base layer 12. A detector 24, eg. a photo detector, can be used to detect the light signals 22 emitted by the upconverting material 18 in order to verify the authenticity of the security document 1.

 It has surprisingly been found that an opacifying coating 14 which contains
20 a highly refractive pigment, eg. TiO_2 , CaCO_3 , BaSO_4 , ZnO , not only disperses the visible light signals 22 emitted by the upconverting material 18, but also enhances or amplifies the emitted signal 22. This has advantageous effects in widening the area over which the signals 22 are detectable and reducing the lower detection limit (about 3 times background noise). This also enables the concentration of the
25 expensive upconverting material 18 in the base substrate 12 to be reduced, which is also advantageous in the case of a security document 1 formed from a transparent base substrate 12 and having a transparent portion or window 15.

A further advantage of the embodiment of Figure 1 is that because the upconverting material 18 is dispersed uniformly throughout the base layer 12, the signals 22 emitted from the upconverting material 18 can be detected at any location on the security document 1. It will, however, be appreciated that signals
5 emitted in the area of the window 15 will not be as strong owing to the absence of the opacifying coating 14 with refractive pigment in that area.

Referring to Figure 2, there is shown a modified embodiment of a security document 2 in accordance with the invention. The security document 2 is similar to that of Figure 1 and corresponding reference numerals have been applied to
10 corresponding parts. Therefore, the security document 2 includes a base layer 12 formed from a transparent polymeric material containing an upconverting fluorescent material 18, opacifying coatings 14, 14¹ on each side of the base layer 12, and indicia 16, 16¹ printed on the opacifying coatings 14.

The security document 2 differs from that of Figure 1 in that further layers of
15 transparent polymeric material 26, 26¹ are provided on each surface of the base layer 12 to form a composite substrate 10¹ with the opacifying coatings 14 applied to the outer surfaces of the polymeric layers 26, 26¹.

The transparent polymeric layers 26, 26¹ may be formed from at least one co-polymer. Examples of suitable polymeric materials include, polypropylene,
20 polyethylene and random co-polymers, such as polybutylene-ter-polymers.

Another difference is shown in broken lines in Figure 2, in that the opacifying coating 14¹ and indicia 16¹ on one side of the substrate 10 (the lower side in Fig. 2) may be applied to cover the entire surface of the opacifying coating 16¹. The opacifying coating 14 and indicia 16 on the other side of the substrate 10¹
25 (the upper side in Fig. 2) are applied to the surface of the polymeric layer 16 in such a manner as to leave an area 23 of the surface of the layer 16 uncovered to form a "half window" 25 on that side of the security document 2. The uncovered area 23 or "half window" 25 enables an observer to view the security device 17

from said other side of the security document 2, but the security device 17 is obscured or at least partially obscured by the opacifying coating 14¹ and indicia 16¹ on said one side of the security document 2. The security device 17 may be provided on the outer surface of either of the polymeric layers 26, 26¹ or even on
5 the outer surface of the base layer 12.

As in the embodiment of Figure 1, the authenticity of the security document 2 may be verified by directing infra red radiation from an infra red source (not shown in Fig. 2) onto the security document 2 and using a detector (also not shown in Fig. 2) to detect light signals emitted from the upconverting material 18
10 dispersed in the base layer 12 of the substrate 10¹.

In the embodiment of Figure 2, it is possible to detect a stronger signal emitted from the area of the half window 25 on the side of the document 2 on which the opacifying coating 14¹ and indicia 16¹ is applied, than the signal emitted in the region of the full window 15 in the embodiment of Figure 1.

15 It will, however, be appreciated that instead of a half window 25, the security document 2 of Figure 2 may have a full window as in the embodiment of Figure 1. It is also possible for the opacifying coatings 14, 14¹ to be applied to cover the entire surfaces of the polymeric layers 26, 26¹ so that no window or half window is provided.

20 Referring to Figure 3, there is shown a further embodiment of a security document 3 in accordance with the invention. The document 3 is similar to the embodiment of Figure 2 and corresponding reference numerals have been applied to corresponding parts. Therefore, the security document 3 has a base layer 12 and layers 26, 26¹ of transparent polymeric material provided on each side of the
25 base layer 12 to form a composite substrate 10¹. Opacifying coatings 14, 14¹ are applied to the outer surfaces of the polymeric layers 26, 26¹ and indicia 16, 16¹ is provided on the opacifying layers 14, 14¹, eg. by printing.

The security document 3 differs from the embodiment of Figure 2 in that the upconverting fluorescent material 18, 18¹ is dispersed in the polymeric layers 26, 26¹ rather than in the base layer 12. It has been found that if the opacifying layers 14, 14¹ are in intimate contact with the polymeric layers in which the upconverting material 18, 18¹ is dispersed, a stronger signal 22 emerges from the security document 3 when the document 3 is exposed to a beam of infra red radiation 21 from an infra red source 20, than the signal emerging from the embodiment of Figure 2.

The security document 3 may include a full window 15 with the opacifying coatings 14, 14¹ and indicia 16, 16¹ being omitted in areas 13, 13¹ of the outer surfaces of the polymeric layers 26, 26¹ leaving the security device 17 in the window 15 visible from both sides of the document 3. Alternatively, the security document 3 may have a half window with only one of the opacifying coatings 14, 14¹ being omitted in the area of the security device 17. It is also possible for the opacifying coatings 14, 14¹ to be applied to cover the entire surfaces of the polymeric layers 26, 26¹ so that no window or half window is present in the security document 3. In these latter cases, it is possible for the base layer 12 of the substrate to be formed from an opaque or translucent material, such as a paper or fibrous material, with the upconverting material 18 provided in the polymeric layers 26, 26¹, as a transparent base layer 12 is not necessarily required when there is no full window in the security document 3.




It will be appreciated that various modifications and alterations may be made to the preferred embodiments described herein without departing from the scope and spirit of the present invention.

It will be understood that the invention disclosed and defined in this specification extends to all alternative combinations of two or more of the individual features mentioned or evident from the text or drawings. All of these different combinations constitute various alternative aspects of the invention.

It will also be understood that the term "comprises" (or its grammatical variants) as used in this specification is equivalent to the term "includes" and should not be taken as excluding the presence of other elements or features.

By its Registered Patent Attorneys
5 **Freehills Carter Smith Beadle**
SECURENCY PTY LTD

9 October 2003



Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/AU04/001365

International filing date: 07 October 2004 (07.10.2004)

Document type: Certified copy of priority document

Document details: Country/Office: AU
Number: 2003905517
Filing date: 09 October 2003 (09.10.2003)

Date of receipt at the International Bureau: 01 November 2004 (01.11.2004)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER: _____**

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.